

TENAX TN

Type: **750**
Geocomposite



TENAX **TN** geocomposites are a combination of TENAX geonets and nonwoven geotextiles. The combination of geotextiles (filtering action) and geonet (drainage and loads distribution) offers a complete system of “filter-drainage-protection”.

Typical applications

Waste disposals; underground structures; retaining walls; gardens and sport fields; road foundations; ground channels.

PHYSICAL CHARACTERISTICS	TEST METHOD	UNIT	TN 750		NOTES
STRUCTURE			2 strands		
POLYMER TYPE			HDPE		
CARBON BLACK			YES		
FOAMING AGENT			NO		
GEOTEXTILE POLYMER			PP		

DIMENSIONAL CHARACTERISTICS	TEST METHOD	UNIT	TN 750		NOTES
THICKNESS at 20 kPa	ISO 9863	mm	5.0	5.0	a
UNIT WEIGHT	ISO 9864	g/m ²	870	890	a
ROLL WIDTH		m	2.05	3.60	a
ROLL LENGTH		m	40.0	50.0	a
ROLL DIAMETER		m	0.55	0.62	a
ROLL VOLUME		m ³	0.63	1.40	a
ROLL GROSS WEIGHT		kg	71.0	156.0	a



GEOTEXTILE CHARACTERISTICS	TEST METHOD	UNIT	TN 750		NOTES
MASS PER UNIT WEIGHT	ISO 9864	g/m ²	120	140	a
OPENING SIZE	ISO 12956	mm	0.08	0.07	a

TECHNICAL CHARACTERISTICS	TEST METHOD	UNIT	TN 750		NOTES
HYDRAULIC FLOW RATE			i = 1.0		
$\sigma_v = 20$ kPa	ISO 12958	m ² /s	1.20E-03		a,b,c
$\sigma_v = 100$ kPa	ISO 12958	m ² /s	1.00E-03		a,b,c
$\sigma_v = 200$ kPa	ISO 12958	m ² /s	9,50E-04		a,b,c
TENSILE STRENGTH	ISO 10319	kN/m	11.5		a,b
ELONGATION AT PEAK	ISO 10319	%	60.0		a,b

NOTES:

- a) Typical values
- b) Machine direction
- c) 2mm HDPE liner boundary condition

Typical Hydraulic Characteristics



0799-CPD-25



The TENAX Laboratory has been created in 1980 and has been continuously improved with the purpose of assuring unequalled technical development of the products and accurate Quality Control.

The TENAX Laboratory can perform mechanical, hydraulic and durability tests, according to the most important international standards like ISO, TNN, ASTM, DIN, BSI, UNI.

TENAX SpA Geosynthetics Division

Via dell'Industria, 3
I-23897 Viganò (LC) ITALY
Tel. (+39) 039.9219307
Fax (+39) 039.9219200
e-mail: geo.div@tenax.net
Web Site: www.tenax.net

TENAX International B.V. Geosynthetics Division

Via Ferruccio Pelli, 14
CH-6900 Lugano SWITZERLAND
Tel. (+41) 091.9242485
Fax (+41) 091.9242489
e-mail: geo@tenax.ch
Web Site: www.tenax.net